

## Product Information

# EcoTek Styrene Free, Low VOC Laminating Resin

### TYPICAL CAST MECHANICAL PROPERTIES\* see back page (1)

Test	Units of Measure	Nominal	Test Method
Tensile Strength	psi/MPa	11,600/80.0	ASTM D 638
Tensile Modulus	psi/GPa	490,000/3.4	ASTM D 638
Tensile Elongation	%	3.5	ASTM D 638
Flexural Strength	psi/MPa	16,300/112	ASTM D 790
Flexural Modulus	psi/GPa	500,000/3.4	ASTM D 790
Heat Distortion Temperature	°F/°C @264 psi	189/87	ASTM D 648

\*Typical properties are not to be construed as specifications.

### TYPICAL LIQUID RESIN PROPERTIES at 25°C see back page (2)

Test	Units of Measure	Nominal Value
Viscosity, Brookfield LV #3 @60 rpm	cps	650
Thix Index, 6/60	-	>2.0
Styrene Content	%	0
Gel Time, 100g, 1.5% MEKP-9H	minutes	40.0
Gel to Peak	minutes	7.0
Peak Temperature	°F/°C	320/160



### DESCRIPTION

H164-ACAG-40 is a medium reactive, styrene free, thixotropic, pre-promoted resin engineered with AOC's patented technology.

### APPLICATION

H164-ACAG-40 is designed for use in the manufacturing of boats and other composite parts using hand lay-up or spray-up application methods. Fast laminate cure allows for faster production rates without the loss of surface profile.

### BENEFITS

- "Green" product, styrene free
- Flash point >200°F
- Non Red Label, DOT rating - non regulated
- Flammability rating Class 1/HMIS and NFPA

[www.green-resins.com](http://www.green-resins.com)  
[green-resins@aoc-resins.com](mailto:green-resins@aoc-resins.com)

# EcoTek™ H164-ACAG-40 Polyester Resin



## PERFORMANCE GUIDELINES

**A.** Keep full strength catalyst levels between 1.25% - 1.75% of the total resin weight.

**B.** Maintaining shop temperatures between 65°F/18°C and 90°F/32°C and humidity between 40% and 90% will help the fabricator make a high quality part. Consistent shop conditions contribute to consistent gel times.

## STORAGE STABILITY

Resins are stable for three months from date of production when stored in the original containers away from sunlight at no more than 70°F/21°C.

During the hot summer months, no more than two months stability at 86°F/30°C should be anticipated. After extended storage, some drift may occur in gel time.

Storage in plastic totes made out materials such as polyethylene (PE) or polypropylene (PP), in particular translucent PE/PP, will accelerate gel formation and result in a significantly reduced storage stability.

Storage of this resin outdoors in translucent plastic totes may reduce the storage stability to only a few weeks. AOC cannot assume responsibility for gel formation under these storage conditions.

## APPLICATION GUIDELINES

Due to the excellent curing characteristics of EcoTek H164-ACAG-40 resin, complete all secondary bonding as soon as possible. Exposing the laminate to sunlight will result in severe secondary bonding problems. After 24 hours of cure, it may be necessary to abrade the laminate to insure good secondary bonding, especially if the surface of the laminate is resin rich. Avoid low fiberglass content and resin puddling with this product.

To assure adequate bonding to gel coats, fabricators should pre-wet the gel coat surface with a thin pass of catalyzed resin prior to lamination.

Chemical resistance studies indicate that resins like H164-ACAG-40 have very poor resistance to certain hydrophobic liquids, such as hydrocarbons. Fuel storage tanks should not be produced with the H164-A resin.

If your manufacturing needs require a more corrosion resistant resin, please contact your AOC representative for information or technical assistance on AOC's line of isophthalic or vinyl ester resins.

## SAFETY

See appropriate Material Safety Data Sheet for guidelines.

## ISO 9001:2000 CERTIFIED

The Quality Management Systems at every AOC manufacturing facility have been certified as meeting ISO 9001:2000 standards. This certification recognizes that each AOC facility has an internationally accepted model in place for managing and assuring quality. We follow the practices set forth in this model to add value to the resins we make for our customers.

## FOOTNOTES

### (1)

Based on tests run at 77°F/25°C and 50% relative humidity. All tests performed on unreinforced cured resin castings. Thixotropic components, if applicable, are excluded from casting samples. Castings were post cured.

### (2)

The gel times shown are typical but may be affected by catalyst, promoter and inhibitor concentrations and resin, mold and shop temperature. Variations in gelling characteristics can be expected between different lots of catalysts and at extremely high humidities. Pigment and fillers can retard or accelerate gelation. It is recommended that the fabricator check the gelling characteristics of a small quantity of resin under actual operating conditions prior to use.

[www.green-resins.com](http://www.green-resins.com)  
[green-resins@aac-resins.com](mailto:green-resins@aac-resins.com)



The information contained in this data sheet is based on laboratory data and field experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any liability for occurrences arising out of its use. The user, by accepting the products described herein, agrees to be responsible for thoroughly testing each such product before committing to production.

Our recommendations should not be taken as inducements to infringe any patent or violate any law, safety code or insurance regulation.